# Innovative lubricants need experienced application engineers

Every lubricant change should be preceded by expert consultation on the application in question. Only then the best lubricant system can be selected. Experienced FUCHS engineers will be glad to advise on products for the application in question and also on our full range of lubricants.

**FUCHS Industrial Lubricants** 

# A Complete Product Line



Contact:

#### FUCHS EUROPE SCHMIERSTOFFE GMBH

Friesenheimer Straße 15 68169 Mannheim /Germany Phone: +49 621 3701-0 Fax: +49 621 3701-570 E-mail: zentrale@fuchs-europe.de www.fuchs-europe.de

Export Division Friesenheimer Straße 9 68169 Mannheim/Germany Phone: +49 621 3701-703 Fax: +49 621 3701-719

12/2009 1.0



# Hydraulic oils



FUCHS EUROPE SCHMIERSTOFFE GMBH

# YOUR STRONG GLOBAL PARTNER FOR INDUSTRIAL LUBRICANTS



# HOW WE EXCEL

We are a German company which manufactures and markets a wide range of lubricants and derived specialties. The company, which was founded in 1931 as RUDOLF FUCHS, is located in Mannheim and is a 100 % subsidiary of FUCHS PETROLUB AG, which is the largest independent lubricants manufacturer worldwide.

Our company's degree of specialisation and innovation is way above the industrial average in this field. The full product line includes almost 2,000 lubricants and derived specialties for all walks of life, industrial processes and applications. Our customer's success is also our success. Because partnership to us means passing-on benefits. The advantage of a strong market presence: FUCHS is the largest independent manufacturer of lubricants in the world. The benefit of premium, innovative products from a full-line manufacturer: With a complete product line as well as tailor-made special solutions, FUCHS has a product for every application. The benefits of reliability: Certified according to DIN EN ISO 9001:2000 and ISO/TS 16949:2002, FUCHS has been continuously upgrading its highly specialised lubricants for decades.

And naturally, partnership for us also means providing our customers with competent support. With comprehensive marketing. With high-performance logistics. With the development of successful service concepts. And qualified consulting. Because together, we can achieve more.

# WHAT INCREASES THE VALUE OF OUR PRODUCTS


We develop lubricants: application-specific and tailor-made for our customer's processes. Together we look for the best lubricants for our customers. This cooperation is unique in terms of its form, scope and intensity. We call it development partnership. The success of our development partnerships is based on an important fact: FUCHS is not one of the oil-giants.



FUCHS is a multinational, independent lubricant manufacturer. Our independence is the difference. We are open to new solutions, open for visions – the prerequisites for innovations. And innovation is the defining characteristic of FUCHS. 70 % of our products are less than five years old and the great majority of our products are individual solutions. Challenge us and see!



# Summary of the various hydraulic oil categories.



While the information and figures given here are typical of current production and confirm to specification, minor variations may occur. Subject to amendment. Edition 12/2009

# We combine technology with ecology.

#### Fire-resistant hydraulic fluids.

HYDROTHERM 46 M is a well-known water-glycol fluid which complies with the 7th Luxembourg Report and has been approved by a host of component manufacturers. It offers extraordinarily long life, extremely good wear protection and high chemical stability.

The PLANTOFLUX AT-S series of HFDU fluids based on selected carbonic acid esters is approved by Factory Mutual in the USA and is used with great success in the iron, steel and aluminium industries.

The fire-resistant hydraulic fluid range is rounded-off with RENOSAFE TURBO 46 DR (phosphoric acid ester) and the water-based HFAE- and HFAS-SOLCENIC products which are used in mining applications.

#### **Special fluids**

Furthermore, we offer a wide range of special hydraulic fluids which satisfy every conceivable demand.

#### **RENOLIN Hydraulic oils – containing zinc**

Name	Corrosion protec- tion	Ageing stability	EP/AW Antiwear additives	Demul- sifying	Detergent	Highly disper- sant	High VI
RENOLIN B	•	•	•	•			
RENOLIN B-HVI	•	•	•	•			•
RENOLIN XtremeTemp	•	• ! !	•	•			•!
RENOLIN D	•	•	•				
RENOLIN MR	•!	• !	•		•	•	
RENOLIN MR 310/520	•!	•1	•		•	•	• !
RENOLIN MR-MC	•!	• ! !	•		•	•	• !
RENOLIN LD	•	•	•		•	• !	

#### **RENOLIN Hydraulic oils – zinc- and ash-free**

Name	Corrosion protec- tion	Ageing stability	EP/AW Antiwear additives	Demul- sifying	Detergent	Highly disper- sant	High VI
RENOLIN DTA	•	•		•			
RENOLIN ZAF-B	•	•	•	•			
RENOLIN ZAF-D	•	•	•		•		
RENOLIN MWB	•	• !	•!!1), 2)		•	•!	
RENOLIN ZAF-DT	•	• !	• !		•	•!	
RENOLIN ZAF-MC	•	• ! !	•	•			• !
RENOLIN ZAF 46 HT	•	•!	•	•			

!= Dominant characteristic (special additive reserves) 1) = Brugger Anti Wear > 50 Nmm<sup>2</sup> 2) = FE8-Roller Bearing Wear test = pass, excellent

While the information and figures given here are typical of current production and confirm to specification, minor variations may occur. Subject to amendment. Edition 12/2009



As one of the pioneers in the area of rapidly biodegradable fluids, our product program includes

PLANTOHYD – Partially saturated esters,

PLANTOSYN – Saturated esters,

PLANTOHYD S-NWG – Non-water-polluting ester products and PLANTOLUBE POLAR – Low-temperature synthetic ester oils.

The PLANTO ENVIRO product series are newly developed, biodegradable hydraulic fluids based on selected ester oils. The products are awarded with the new European Eco Label ("Euro marguerite") and surpass the highest technical and ecological requirements with regard to excellent biodegradability, low toxicity, excellent performance. The raw materials are based on renewable sources: PLANTO ENVIRO HYD 46 S, PLANTO ENVIRO HYD 46 HVI

# The optimum fluid for every application – and the optimum solution for every problem.

Please don't hesitate to contact our application engineers.

**Product name** 

**RENOLIN DTA 2** 

**RENOLIN DTA 5** 

**RENOLIN DTA 7** 

**RENOLIN DTA 10** 

**RENOLIN DTA 15** 

**RENOLIN DTA 22** 

**RENOLIN DTA 32** 

**RENOLIN DTA 46** 

**RENOLIN DTA 68** 

**RENOLIN DTA 100** 

**RENOLIN DTA 150** 

**RENOLIN DTA 220** 

**RENOLIN DTA 320** 

**RENOLIN DTA 460** 

**RENOLIN DTA 680** 

**Product name** 

# **Specialties for the specialist – an overview.**

Flash point Cleveland °C

100

120

155

174

195

210

222

228

250

248

266

280

280

315

302

Kinematic

viscosity at 40 °C

mm<sup>2</sup>/s

2,2

4,6

7,4

10

15

22

32

46

68

100

150

220

320

460

680

Flash Kinematic Kinematic

Kinematio

viscosity at 100°C

mm<sup>2</sup>/s

\_

1,6

2,2

2,6

3,4

4,2

5,4

6,8

8,7

11,2

15,5

18,8

24,0

30,4

37,9

Density at 15°C kg/m<sup>3</sup>

805

837

839

851

856

865

874

874

882

881

889

893

898

904

913

Density

#### **RENOLIN DTA – DTA – demulsifying general lubricating,** spindle and hydraulic oils

Description

Spindle, hydraulic and general

lubricating oils (machine oils)

containing selected base oils

and additives to improve ag-

eing stability and corrosionprotection. All RENOLIN DTA

products are DIN 51524-1 (HL)

hydraulic oils and DIN 51517-2

(CL) general lubricating oils, based on mineral oils, demul

sifying (water-repellent) and free of zinc.

ISO 6743/4, HL,

ISO 6743-6 and ISO 12925-1: CKB.



iscosity index VI

\_

106

103

92

98

94

102

101

99

97

94

95

95

95

92

Pour point °C

-27

-40

-27

-27

-27

-27

-24

-24

-18

-18

-15

-12

-12

-12

-12

Main application area

For thermally-stressed bea-

rings and hydraulic systems

with peak temperatures of

General lubrication without

specific wear protection demands (without AW/EP)

(Consult product informa-

tion 4-1292 for further

details)

approx. 120 °C.

#### **RENOLIN B HVI – high performance emulsifying AW/EP hydraulic oils** with a high Viscosity Index , Denison HFO approved

Product name	Description	Density at 15°C kg/m³	Flash point Cleveland °C	Kinematic viscosity at 40°C mm²/s	Kinematic viscosity at 100°C mm²/s	Viscosity index VI	Pour- point °C	Main application area				
<b>RENOLIN B 15 HVI</b>	Hydraulic and general lubri-	859	180	15	3,8	151	-45	RENOLIN B-HVI oils	ing)			
RENOLIN B 32 HVI	cating oils (machine oils) with a high Viscosity Index and additives to improve ageing	a high Viscosity Index and	a high Viscosity Index and	a high Viscosity Index and	871	178	32	6,3	152	-48	are suitable for all hydraulic systems,	lsify
<b>RENOLIN B 46 HVI</b>	resistance, corrosion protec-	879	186	46	8,1	149	-45	especially when a high viscosity index	emu			
RENOLIN B 68 HVI	tion and wear protection. Mi- neral oil-base and containing zinc, RENOLINB-HVI oils are HVLP hydraulic and general lubricating oils according to DIN 51 524-3. ISO 6743/4, HV ISO 11158, HV Denison HF0, HF1, HF2	882	210	68	11,0	154	-42	is specified or if ex- cess viscosity during start-ups or insuffi- cient viscosity at operating tempera- tures is a problem. High VI provides multigrade characteristics. "Energy-saving- fluids", high- efficiency fluids. (Consult product information 4-1222 for further details)	HVLP oils (demulsifying)			

#### **RENOLIN B – high performance demulsifying AW/EP hydraulic** and general lubricating oils, Denison HF0 approved

Description



#### **RENOLIN XtremeTemp – high performance multigrade hydraulic fluid based on** "New Generation" of base oils, shear stable, extended lifetime

Product name	Description	Density at 15°C kg/m³	Flash point Cleveland °C	Kinematic viscosity at 40°C mm²/s	Kinematic viscosity at 100°C mm²/s	Viscosity index VI	Pour- point °C	Main application area	
RENOLIN XtremeTemp 32	Universal, high performance hydraulic fluids with high	861	216	32	6,9	185	-33	Universal high performance multi-	(vina)
RENOLIN XtremeTemp 46	Viscosity Index and excellent shear stability (VI ≥ 180), based on selected hydro- treated base oils, high ageing stability, excellent corrosion protection, extended lifetime,	865	234	49	9,3	180	-34	grade hydraulic fluids for stationary and mobile hydraulic systems, improvement of efficiency.	oils (demulsifvina)
	excellent wear protection, fulfil and surpass DIN 51 524-3, HVLP, ISO 6743/4, HV, ISO 11158, HV, Denison HFO, HF1, HF2							"Energy-saving- fluids", high- efficiency fluids, shear-stable visco- sity index.	HVLP
								(Consult Product Information 4-1088 for further details).	

RENOLIN RENOLIN RENOLIN RENOLIN RENOLIN RENOLIN RENOLIN

		at 15°Ć kg/m³	point Cleveland °C	viscosity at 40 °C mm²/s	viscosity at 100°C mm²/s	index VI	point °C	application are
B 3 VG 10	General lubricating and hy-	856	178	10	2,6	96	-30	As lubricating oils but also
B 5 VG 22	draulic oils with good ageing resistance and additives to	863	180	22	4,4	107	-27	as hydraulic oils if good ageing resistance, wear pro-
B 10 VG 32	improve corrosion protection. Good viscosity temperature	876	205	32	5,5	109	-24	tection and demulsifying properties are required.
B 15 VG 46	behaviour, good wear protec- tion, demulsifying, good air	875	210	46	6,9	105	-24	Universal hydraulic oils for all systems, even if
B 20 VG 68	release, contain zinc. The RENOLIN B series fulfil	881	224	68	8,8	100	-24	thermally-stressed. Excel- lent filtration behaviour.
B 30 VG 100	and surpass the minimum de- mands on HLP hydraulic oils	881	232	100	11,1	96	-18	(Consult product infor-
I B 40 VG 150	according to DIN 51 524-2. ISO 6743/4, HM ISO 11158, HM Denison HF0, HF1, HF2	887	224	150	14,5	94	-15	mation 4-1207 for further details)

\* PI = Product information EP = Extreme pressure additives, to avoid wear seizures and scuffing at high pressures and loads AW = Anti wear additives, to avoid wear in boundary friction c

While the information and figures given here are typical of current production and confirm to specification, minor variations may occur. Subject to amendment. Edition 12/2009

- \* PI = Product information EP = Extreme pressure add
- = Extreme pressure additives, to avoid wear seizures and scuffing at high pressures and loads AW = Anti wear additives, to avoid wear in boundary friction cond

While the information and figures given here are typical of current production and confirm to specification, minor variations may occur. Subject to amendment. Edition 12/2009





**Product name** 

**RENOLIN D 2** 

**RENOLIN D 3** 

**RENOLIN D 5** 

**RENOLIN D 10** 

**RENOLIN D 15** 

**RENOLIN D 20** 

**RENOLIN D 30** 

**Product name** 

## **Specialties for the specialist – an overview.**

Density at 15°C kg/m<sup>3</sup>

844

852

870

872

875

878

882

10

22

32

46

68

100

2,8

4,3

5,4

6,8

8,7

11,3

Kinematic viscosity at 100°C

Viscosity index VI

Kinematic viscosity at 40°C

178

200

210

224

232

253

#### **RENOLIN D – detergent AW/EP hydraulic and general lubricating oils**

Description

Detergent hydraulic and

general lubricating oils with

additives to improve ageing

resistance, corrosion protec-

Favourable viscosity-tempera-ture behaviour. Contain zinc.

**RENOLIN D products fulfil and** 

surpass the minimum demands

on HLPD hydraulic oils accor-ding to DIN 51 524-2.

ISO 6743/4-HM with

DD-performance.

Description

tion and wear protection.



96

100

102

101

99

99

-30

-27

-24

-27

-24

-21

lubricating oils but especially as hydraulic oils when good ageing resistance, good wear protection, detergency and demulsifying properties are required. Universal hydraulic oils for all systems, even if thermally-stressed. (Consult Product Information 4-1010 for further details)

RENOLIN MR 310/520/1030 – detergent AW/EP hydrau
with an extremely high Viscosity Index

Product name	Description	Density at 15 °C kg/m³	Flash point Cleveland °C	Kinematic viscosity at 40°C mm²/s	Kinematic viscosity at 100°C mm²/s	Viscosity index VI	Pour- point °C	Main application area	ant)
RENOLIN MR 310	Hydraulic and lubricating	855	120	15	5,4	360	-48	RENOLIN MR 310,	pers
RENOLIN MR 520	oils with extremely high Viscosity Index and outstan-	867	170	32	9,0	270	-56	520 and 1030: For all hydraulic sy-	t/dis
RENOLIN MR 1030	ding cleaning and sludge transportation properties. HVLPD according to DIN 51 502 together with DIN 51 524. ISO 6743/4, HV	873	214	68	11,0	154	-36	stems which are subject to larger temperature fluctu- ations or which are operated outdoors (e.g. canal locks and weir machinery). (Consult Product Information 4-1054 for further details)	HVLPD oils (detergent/dispersant)

#### **RENOLIN MR – high detergent AW/EP general lubricating and hydraulic oils** with excellent corrosion protection

Density at 15°C kg/m<sup>3</sup>



Main application area

#### **RENOLIN MR MC – high performance shear-stable AW/EP hydraulic and** lubricating oils containing special base oils - high Viscosity Index

Product name	Description	Density at 15°C kg/m³	Flash point Cleveland °C	Kinematic viscosity at 40°C mm²/s	Kinematic viscosity at 100°C mm²/s	Viscosity index VI	Pour- point °C	Main application area	ant)
RENOLIN MR 22 MC	Universal lubricating and hy-	856	200	22	4,9	153	-54	RENOLIN MR MC:	persi
RENOLIN MR 32 MC	draulic oils containing high Viscosity Index (shear-stable)	858	220	32	6,4	152	-48	The same applica- tions as for RENOLIN	t/dis
RENOLIN MR 46 MC	MC base oils. Excellent oxida- tion stability and powerful	864	234	46	8,3	154	-48	MR in addition to those which require	rgen
RENOLIN MR 68 MC	cleaning and sludge-trans- portation properties. HVLPD according to DIN 51 524-3. MR 22 MC: HVLP (HV) 22 MR 32 MC: HVLP (HV) 32 MR 46 MC: HVLP (HV) 46 MR 68 MC: HVLP (HV) 68 ISO 6743/4, HV	870	253	68	11,2	157	-42	detergent oils with very high shear sta- bility. Allow oil change intervals to be extended, grades to be rationalized. Multigrade characte- ristics. Very wide temperature range. "Energy-saving fluids", high-ef- ficiency fluids. (Consult Product Information 4-1249 for further details)	HVLPD oils (detergent/dispersant)

\* PI = Product information EP = Extreme pressure additives, to avoid wear seizures and scuffing at high pressures and loads

AW = Anti wear additives, to avoid wear in boundary friction condi

While the information and figures given here are typical of current production and confirm to specification, minor variations may occur. Subject to amendment. Edition 12/2009

\* PI = Product information EP = Extreme pressure additives, to avoid wear seizures and scuffing at high pressures and loads AW = Anti wear additives, to avoid wear in boundary friction conditions

While the information and figures given here are typical of current production and confirm to specification, minor variations may occur. Subject to amendment. Edition 12/2009

Î

HLPD oils (deter

			°C	mm²/s	mm²/s			
RENOLIN MR 0 VG 2	RENOLIN MR products are	807	75	2,2	-	-	-42	RENOLIN MR 3: For ma-
RENOLIN MR 1 VG 5	special HLPD lubricating and hydraulic fluids according to	837	85	5	1,7	83	-36	chine tool spindles and bobbin bearings in the tex-
RENOLIN MR 3 VG 10	DIN 51 502 with outstanding corrosion protection, powerful	852	166	10	2,6	91	-30	tile industry. RENOLIN MR 5, 10 and 20: Heavy-duty
RENOLIN MR 5 VG 22	cleaning and sludge trans- portation properties. Contain	868	165	22	4,3	105	-30	hydraulic oils with good corrosion protection up to
RENOLIN MR 10 VG 32	zinc as well as being detergent and dispersant. RENOLIN MR	875	210	32	5,4	102	-30	continuous temperatures of 100 °C. RENOLIN 5, 10 and
RENOLIN MR 15 VG 46	oils are used in a number of hydraulic systems as problem	877	220	46	6,9	105	-27	20: For smaller gearboxes, especially when fitted with
RENOLIN MR 20 VG 68	solvers, especially when stan- dard oils cannot fulfil all the	881	225	68	8,9	105	-24	electromagnetic clutches. RENOLIN MR 30: For larger
RENOLIN MR 30 VG 100	requirements. RENOLIN MR products fulfil and surpass the	883	248	100	11,4	100	-18	gearboxes. Running-in and corrosion protection oil.
RENOLIN MR 40 VG 150	minimum demands on HLPD hydraulic oils according to	889	250	150	14,8	98	-18	RENOLIN MR series allows oil changes to be extended.
RENOLIN MR 90 VG 320	DIN 51 524-2.	903	265	320	24,8	99	-12	(Consult Product Infor-
RENOLIN MR 140 VG 460	ISO 6743/4-HM with high DD-performance.	907	297	460	31,0	95	-9	mation 4-1249 for further details)

Flash point Cleveland

## aulic and lubricating oils





# **Specialties for the specialist – an overview.**

#### **RENOLIN LD – universal functional fluid with cleaning** and flushing properties



and ash-free HVLP oils (demulsifying)

Product name	Description	Density at 15°C kg/m³	Flash point Cleveland °C	viscosity	Kinematic viscosity at 100°C mm²/s	Viscosity index VI	Pour- point °C	Main application area
RENOLIN LD 10	Specially refined oil with addi- tives to increase ageing resi- stance, corrosion protection, EP performance and wear protection. Excellent cleaning and sludge transportation.	877	220	46	6,9	105	-27	A functional fluid with cleaning and flushing properties for general lubri- cation and hydraulic systems. Elimi- nates gumming caused by dragged-in cutting fluids. Machines can continue to run normally during cleaning and flushing. However, an oil change is recommended as soon as all conta- minants are dislodged.

## **RENOLIN ZAF D – detergent, AW/EP, zinc- and ash-free hydraulic oils**

Product name	Description	Density at 15°C kg/m³	Flash point Cleveland °C	Kinematic viscosity at 40°C mm²/s	Kinematic viscosity at 100°C mm²/s	Viscosity index VI	Pour- point °C	Main application area	HLPD oils t)
RENOLIN ZAF 22 D	Zinc- and ash-free lubricating	866	204	22	4,4	98	-30	Detergent, zinc- and ash-free	e e
RENOLIN ZAF 32 D	and hydraulic oils with deter- gent and dispersant additives.	874	210	32	5,3	98	-27	hydraulic and general lubrica- ting oils for all hydraulic drives	s Ė 🦉
RENOLIN ZAF 46 D	Good ageing resistance. Red- uce wear and inhibit corrosion.	876	230	46	7,1	106	-24	even if thermally stressed. Red- uce environ mental pollution	and as (de <sup>.</sup>
RENOLIN ZAF 68 D	HLPD according to DIN 51 524-2 HM according to ISO 6743/4	883	226	68	8,7	97	-19	and waste water-treatment costs.	Zinc- a
	(Except demulsifying properties)								N

**RENOLIN ZAF MC – zinc- and ash-free, shear-stable, AW/EP high performance hydraulic** oils containing selected base oils, excellent oxidation stability and a high Viscosity Index



Product name	Description	Density at 15°C kg/m³	Flash point Cleveland °C	Kinematic viscosity at 40°C mm²/s	Kinematic viscosity at 100°C mm²/s	Viscosity index VI	Pour- point °C	Main application area
<b>RENOLIN ZAF 32 MC</b>	Lubricating and hydraulic oils	840	246	35	6,7	149	-45	Shear stable, zinc- and ash-free hy-
<b>RENOLIN ZAF 46 MC</b>	containing MC base oils and selected additives. Very good	843	238	46	8,0	148	-45	draulic and general lubricating oils with a high Viscosity Index. These
RENOLIN ZAF 68 MC	oxidation and ageing stability, very good corrosion protection and good wear protection. High Viscosity Index (shear-stable). Fulfil and surpass DIN 51524-3; ISO 11158, HV ZAF 32 MC: HVLP 32; ZAF 46 MC: HVLP 46; ZAF 68 MC: HVLP 68	854	238	68	10,6	146	-42	products contain MC base oils. Allow oil change intervals to be extended and grades to be rationalized (multi- grade characteristics). "Energy-saving-fluids", high-efficiency fluids. (Consult Product Information 4-1055 for further details)

## RENOLIN MBW - zinc- and ash-free, EP/AW hydraulic oils with excellent wear protection (high Brugger values) and good oxidation stability

Product name	Description	Density at 15°C kg/m³	Flash point Cleveland °C	viscosity	Kinematic viscosity at 100°C mm²/s	Viscosity index VI	Pour- point °C	Main application area
RENOLIN MWB 46	Selected solvent extracts with	882	218	46	6,9	105	-24	Heavy-duty, hydraulic and
RENOLIN MWB 68	additives to improve oxidati- on and ageing resistance. Excellent corrosion and wear protection, good EP perfor- mance, lower coefficient of friction. Excellent protection against wear. High perfor- mance reserves. HLPD according to DIN 51 524-2 (except demulsifying properties) CLP according to DIN 51 517-3 CKC according to ISO 6743/6	879	224	68	8,7	99	-18	lubricating oils for all highly- stressed hydraulics. Excellent wear protection. Good EP performance. High Brugger values (> 50 N/mm <sup>2</sup> ).



#### **RENOLIN ZAF DT – highly detergent, zinc- and ash-free, EP/AW hydraulic oils** with excellent wear protection

Product name	Description	Density at 15°C kg/m³	Flash point Cleveland °C	Kinematic viscosity at 40 °C mm²/s	Kinematic viscosity at 100 °C mm²/s	Viscosity index VI	Pour- point °C	Main application area
RENOLIN ZAF 5 DT	Selected solvent extracts with	847	116	5	1,7	99	-40	Heavy-duty, hydraulic and
RENOLIN ZAF 10 DT	special additives to improve corrosion and wear protection. Good EP and Brugger perfor- mance. Detergent and disper- sant formulations. Fulfil and surpass DIN 51 524-2 (except	848	154	10	2,7	108	-30	lubricating oils with outstan- ding detergent and disper-
RENOLIN ZAF 15 DT		865	190	15	3,3	86	-27	sant properties. Very good ageing resistance, good
RENOLIN ZAF 22 DT		866	198	22	4,4	109	-27	corrosion protection and excellent EP performance. (Consult Product Information
RENOLIN ZAF 32 DT	demulsifying properties) ISO 11158, HM	876	210	32	5,4	102	-24	
RENOLIN ZAF 46 DT	CLP according to DIN 51 517-3 CKC according to ISO 6743/6	876	218	46	6,8	101	-24	4-1125 for further details)
RENOLIN ZAF 68 DT		879	224	68	8,9	104	-18	
RENOLIN ZAF 100 DT		882	220	100	11,3	99	-18	
RENOLIN ZAF 150 DT		887	222	150	14,6	96	-15	

PI = Product information
EP = Extreme pressure additives, to avoid wear seizures and scuffing at high pressures and loads
AW = Anti wear additives, to avoid wear in boundary friction conditions

While the information and figures given here are typical of current production and confirm to specification, minor variations may occur. Subject to amendment. Edition 12/2009

## **RENOLIN ZAF B – demulsifying, AW/EP, zinc- and ash-free hydraulic oils**

Product name	Description	Density at 15°C kg/m³	Flash point Cleveland °C	Kinematic viscosity at 40°C mm²/s	Kinematic viscosity at 100°C mm²/s	Viscosity index VI	Pour- point °C	Main application area
RENOLIN ZAF 5 B	Zinc- and ash-free lubricating-	847	160	4,6	1,6	95	-39	Demulsifying, zinc- and ash-free
RENOLIN ZAF 10 B	and hydraulic oils with good ageing resistance. They con- tain additives which reduce wear and inhibit corrosion. HLP according to DIN 51524-2 HM according to ISO 6743/4 HM according to ISO 11158	851	170	10	2.6	94	-30	hydraulic and general lubricating oils with good ageing resistance for all
RENOLIN ZAF 22 B		865	212	22	4,3	100	-30	hydraulic drives even if thermally stressed. Reduce environmental pol-
RENOLIN ZAF 32 B		872	215	32	5,4	102	-30	lution and waste water-treatment costs.
<b>RENOLIN ZAF 46 B</b>		875	234	46	6,8	101	-27	
RENOLIN ZAF 68 B		879	230	68	8,7	102	-21	
RENOLIN ZAF 100 B		882	240	100	11,3	99	-18	
RENOLIN ZAF 150 BB		886	225	150	14,6	94	-21	
RENOLIN ZAF 220 BB		894	240	220	18,6	94	-9	

\* PI = Product information EP = Extreme pressure additives, to avoid wear seizures and scuffing at high pressures and loads AW = Anti wear additives, to avoid wear in boundary friction conditions

While the information and figures given here are typical of current production and confirm to specification, minor variations may occur. Subject to amendment. Edition 12/2009

# RENOLIN





# **Specialties for the specialist – an overview.**

#### PLANTO ENVIRO – new developed biodegradable hydraulic fluids according the new European Eco Label "Euro Marguerite"

NEW

E

Product name	Description	Density at 15°C kg/m³	Flash point Cleveland °C	Kinematic viscosity at 40°C mm²/s	Kinematic viscosity at 100°C mm²/s	Viscosity index VI	Pour- point °C	Main application area
PLANTO ENVIRO HYD 46 S	PLANTO ENVIRO HYD 46 S is a rapidly biodegradable and environmentally friendly high- performance hydraulic fluid based on synthetic esters, type HEES. It has been awarded the European Eco-Label EEL. ISO 15380: Type HEES, EEL 2005/360/EC The changeover-guidelines set out in ISO 15380 should be observed.	920	280	46	9,1	185	-46	PLANTO ENVIRO HYD 46 S was specially developed for mobile ag- ricultural, forestry and construction equipment for which ISO 15380 hydraulic fluids are specified. PLANTO ENVIRO HYD 46 S is the ideal product for machinery wor- king in environmentally sensitive areas such as Protected Water Zones and for earthworks in gene- ral. Application: - 35°C to 90°C ISO 15380: Type HEES, EEL 2005/360/EC
PLANTO ENVIRO HYD 46 HVI	PLANTO ENVIRO HYD 46 HVI is an environmentally friendly, rapidly biodegradable hydrau- lic fluid offering the highest performance, type fully satura- ted ester. It can be used in all hydraulic systems, even the most highly stressed. PLANTO ENVIRO HYD 46 HVI exceeds the requirements of ISO 15380 and has been awarded the European Eco- Label EEL. ISO 15380 : Type HEES, EEL 2005/350/EC	906	280	46	8,0	147	-36	PLANTO ENVIRO HYD 46 HVI is fully compatible with all materials commonly used in hydraulic ma- chinery and is a perfect substitute for mineral oil-based and synthetic hydraulic fluids. It is perfectly sui- table for all applications in mobile and stationary hydraulic systems for which a rapidly biodegradable hydraulic oil according to ISO 15380: HEES is recommended and particularly when spillages can cause pollution to soil, groundwa- ter or rivers and when a hydraulic oil is required with outstanding thermal and ageing stability as well as material compatibility. The changeover guidelines set out in ISO 15380 should be observed.

#### PLANTOHYD S und PLANTOSYN HVI ester-based, environmentally harmless hydraulic fluids

Product name	Description	Density at 15°C kg/m³	Flash point Cleveland °C	Kinematic viscosity at 40°C mm²/s	Kinematic viscosity at 100°C mm²/s	Viscosity index VI	Pour- point °C	Main application area		
PLANTOHYD 15 S	Synthetic ester oils with addi- tives to increase ageing stabi- lity. Rapidly biodegradable, > 90 % in 14 days. PLANTOHYD S and PLANTOSYN	927	225	15	4,0	161	-51	Universally applicable as hydraulic or gene- ral lubricating oils. Especially in situa- tions where environ-		
PLANTOHYD 22 S	offer excellent natural wear protection (FZG Stage 12). 15 S: HEES 15 22 S: HEES 22 32 S: HEES 32	926	240	22	5,4	191	-36	mental protection is a priority. Temperature range: - 35 °C to 90 °C. Changeover guide- lines ISO 15380		
PLANTOHYD 32 S	46 S: HEES 46 68 S: HEES 68	921	246	32	7,1	188	-51	should be observed.		
PLANTOHYD 46 S		according to ISO 15380	921	304	49	9,6	186	-42	PLANTOSYN HVI pro- ducts are recommen-	
PLANTOHYD 68 S		927	304	68	12,2	177	-48	ded when temperature range, ageing stability		
PLANTOHYD 22 S NWG	Synthetic ester oils which are not classified as water-pollu-	905	195	22	5,5	191	-36	and material compati- bility are priorities.		
PLANTOHYD 46 S NWG	ting according to German law.	922	290	46	9,6	192	-39	PLANTOHYD and PLANTOSYN oils out-		
PLANTOSYN 46 HVI		905	290	46	8,1	150	-33	perform mineral oil- based hydraulic oils in a number of areas. (Consult Product Information 4-1101 for further details)		

#### PLANTOHYD N – vegetable oil-based, environmentally harmless hydraulic fluids



#### **PLANTOLUBE POLAR -**

ester-based, environmentally harmless, low-temperature hydraulic fluids

Product name	Description	Density at 15°C kg/m³	Flash point Cleveland °C	Kinematic viscosity at 40°C mm²/s	Kinematic viscosity at 100°C mm²/s	Viscosity index VI	Pour- point °C	Main application area	
PLANTOLUBE POLAR 15 S	PLANTOLUBE POLAR S oils are environmentally harmless, rapidly biodegradable and have an extremely low pourpoint. With their very high VI, they cover a wide range of temperatures and can be used as all-season oils. PLANTOLUBE POLAR S oils offer outstanding corrosion- and wear-protection. HEES15 HEES22 according ISO 15380, changeover guidelines ISO 15380 should be observed	899	156	15	4,1	199	<-48	PLANTOLUBE POLAR S oils are	
PLANTOLUBE POLAR 22 S		908	166	22	5,7	200	<-51	recommended for gearboxes, bearings and adjusting mecha-	
								nisms which are subject to extremely low temperatures (e.g. in polar regi- ons, refrigerated warehouses, etc.) and for hydraulic systems operated in similar conditions. (Consult Product Information 4-1098 for further details)	

egradable oils HETG

**Biodegradable oils HEES** 

Flash point Cleveland °C Main application area Kinematic viscosity at 100 °C Density at 15°C kg/m³ iscosity/ index VI viscosity at 40°C poin. °C mm<sup>2</sup>/s mm²/s **PLANTOHYD 40 N** Vegetable oil-based hydraulic fluid with additives to in-922 > 306 44 9,6 223 -36 Universally applicable in hydraulic systems from – 27 °C to 70 °C. crease oxidation and ageing Ð stability. Rapidly biodegradable, Changeover guidelines ISO 15380 should be > 90 % in 14 days. observed. 40N; HETG46 (Consult Product according to ISO 15380 Information 4-1102 for further details)

**Kinematic** 

**Product name** 

PI = Product information
EP = Extreme pressure additives, to avoid wear seizures and scuffing at high pressures and loads
AW = Anti wear additives, to avoid wear in boundary friction conditions

Description

\* PI = Product information EP = Extreme pressure additives, to avoid wear seizures and scuffing at high pressures and loads AW = Anti wear additives, to avoid wear in boundary friction conditions

While the information and figures given here are typical of current production and confirm to specification, minor variations may occur. Subject to amendment. Edition 12/2009

# RENOLIN





## **Further specialties.**

#### **FUCHS Industrial Lubricants**

# Viscosity-temperature diagram.

**RENOLIN UNISYN OL-series** – Fully-synthetic compressor and hydraulic oils based on PAO (polayalphaolefins) with excellent hydraulic performance. Multigrade characteristics, high natural VI (shear-stable), outstanding low temperature properties, good ageing stability, good wear protection.

RENOLIN LIFT-series – Friction-reducing fluids. Mineral-based hydraulic oils containing special additives to avoid stick-slip. Low coefficients of friction, good detergency and good sludge transportation.

**RENOLIN DO 22 HV** – Special hydraulic fluid based on selected base oils with extreme high Viscosity Index (VI = 359). RENOLIN DO 22 HV has a low friction coefficient, has excellent low temperature properties and high ageing stability.

**RENOLIN HLP 46 ALU** – Special, synthetic hydraulic oil with excellent aluminium compatibility. Non-staining oil, good wear protection, good ageing stability.

**RENOLIN MRX-series** – Cleaning and corrosion protection oils. Special hydraulic oils with improved cleaning and corrosion protection characteristics.

RENOLIN ZAF 46 HT – Zinc- and ash-free, high-temperature HLP hydraulic oil. Good demulsification (water-separation) and good oxidation stability.

HYDROTHERM 46 M - Fire-resistant, water-glycol, Type HFC hydraulic oil. Conforms to the demands of the 7th Luxembourg Report. Excellent corrosion and wear protection. BOSCH REXROTH approved for high-pressure applications. (Flushing and protection oil - Hydrotherm PK).

HYDROTHERM 68 LW – Fire-resistant hydraulic fluid, type HFCE – water/glycol, according 7th Luxembourg Report, excellent corrosion protection, excellent anti wear properties. (Water content 20% =HFCE)

RENOSAFE DU 46 - Fire-resistant, water-free hydraulic oil. Type HFDU, polyol ester, suitable for use in VOITH converters.

PLANTOFLUX AT-S-series – Fire-resistant, water-free hydraulic oils. Type HFDU, polyol ester, rapidly biodegradable, Factory Mutual Approved (USA). Conforms to the demands of the 7th Luxembourg Report.

RENOSAFE TURBO 46 DR - Fire-resistant, water-free hydraulic oil. Type HFDR, phosphoric acid ester, hydrolytically-stable. Control circuit fluid for steam and gas turbines.

FUCHS – Lubricants and hydraulic oils for the foodstuff and pharmaceutical industries (NSF-H1 approved). A comprehensive range of hydraulic and lubricating oils based on special white oils or synthetic components (PAO). Just call us!

